

TEST REPORT
(시험 성적서)

신청기관 (인) : (주) 피에스엠씨
APPLICANT : PSMC CO., LTD.
주소 (한글) : 경기도 화성시 향남읍 발안공단로 4길 16
ADDRESS (ENGL.) : 16, Barangongdan-ro 4-gil, Hyangnam-eup, Hwaseong-si,
Gyeonggi-do, Korea

발행면수 (PAGE) : 1 of 11
발행일자 (DATE) : 2022. 05. 09.

시험성적서 번호 (REPORT NO.) : RT22R-S2395-K

시료 명세 : 시료에 대한 상세한 정보는 아래와 같음
(SAMPLE DESCRIPTION) (The following submitted sample(s) said to be)

제품명/형식 : Cu Alloy PMC90 + Ag Plating
(NAME/TYPE OF PRODUCT) (Cu Alloy PMC90 + Ag Plating)

시료고유번호 : RT22R-S2395
(SAMPLE ID NO.) (RT22R-S2395)

제품 생산자/공급자 : (주) 피에스엠씨
(MANUFACTURER/VENDOR)(PSMC CO., LTD.)

시료접수일자 : 2022. 04. 29.
(SAMPLE RECEIVED) (Apr. 29, 2022)

시험일자 : 2022. 04. 29. ~ 2022. 05. 09.
(TESTING DATE) (Apr. 29, 2022 ~ May 09, 2022)

시험방법 : 이 시험성적서의 다음 페이지 첨부
(TEST METHOD) (Please see the following page)

시험결과 : 이 시험성적서의 다음 페이지 첨부
(TEST RESULT) (Please see the following page)

- 비고 (Notes) :
- 이 시험성적서는 제시된 시료 및 시료명으로 시험한 결과로서 유사 대상시료에 적용할 수 없음.
(The test results presented in this report refer only to the object tested.)
 - 이 시험성적서는 승인없이 복사 사용을 금함.
(This report shall not be reproduced except in full without the written approval of the testing laboratory.)
 - 이 성적서는 KOLAS 인청과 무관함.
(This report is not related to the scope of Korea laboratory accreditation scheme.)

승인자 (Approved by)



송명복 / 기술책임자
(M.B.Song / Lab. Technical Manager)

권한자 (Authorized by)



이응용 / 소장
(E.Y.Lee / Lab. General Manager)



Authenticity check

Intertek Testing Services Korea Ltd.
Seoul Office: Tel : 02-6090-9500 Fax : 02-3409-0025 Web Site : intertek.co.kr
Seoul Lab. Address : 7, Ahasan-ro 5-gil, Seongdong-gu, Seoul, 04793 Korea
Ulsan Lab. Address : 34, Yongam-gil, Chongryang-myeon, Ulju-gun, Ulsan 44989 Korea



※ You can verify the forgery and authenticity by the barcode at the end of this document.

TEST REPORT
(시험 성적서)

발행면수 (PAGE) : 2 of 11

발행일자 (DATE) : 2022. 05. 09.

시험성적서 번호 (REPORT NO.) : RT22R-S2395-K

시료고유번호 (SAMPLE ID NO.) : RT22R-S2395

시료명 (SAMPLE DESCRIPTION) : Cu Alloy PMC90 + Ag Plating
(Cu Alloy PMC90 + Ag Plating)

시험항목 (TEST ITEM)	단위 (UNIT)	분석방법 (TEST METHOD)	검출한계 (MDL)	시험결과 (RESULT)
카드뮴 (Cadmium, Cd)	mg/kg	With reference to IEC 62321-5 Edition 1.0 : 2013, by acid digestion and determined by ICP-OES	0.5	N.D.
납 (Lead, Pb)	mg/kg		5	N.D.
수은 (Mercury, Hg)	mg/kg	With reference to IEC 62321-4 : 2013/AMD1 : 2017, by acid digestion and determined by ICP-OES	2	N.D.
6가 크롬 (Hexavalent Chromium, Cr ⁶⁺) (For metal)	μg/cm ²	With reference to IEC 62321-7-1 Edition 1.0 : 2015, by boiling water extraction and determined by UV-VIS Spectrophotometer	0.10	Negative

Tested by : EH Cha, KH Kim

Notes : mg/kg = ppm = parts per million (함량 표시 : 백만분의 일)

μg/cm² = microgram per square centimeter

< = Less than (결과 값 이하)

N.D. = Not detected (< MDL, 미검출 - 검출한계 이하)

MDL = Method detection limit (검출한계)

Remarks : Interpretation of Cr⁶⁺ results

Qualitative result	Concentration of Cr ⁶⁺ (μg/cm ²)	Meaning
Negative	< 0.10	The sample coating is considered a non-Cr ⁶⁺ based coating.
Inconclusive	0.10 ≤ and ≤ 0.13	Unavoidable coating variation may influence the determination.
Positive	> 0.13	The sample coating is considered to contain Cr ⁶⁺ .

1. The qualitative results should be determination by the average result of three test results.
(If concentration of Cr⁶⁺ is over 0.10μg/cm²)
2. The above results will be carried out by visual comparison only with the standard.

Intertek Testing Services Korea Ltd.

Seoul Office: Tel : 02-6090-9500 Fax : 02-3409-0025 Web Site : intertek.co.kr

Seoul Lab. Address : 7, Ahasan-ro 5-gil, Seongdong-gu, Seoul, 04793 Korea

Ulsan Lab. Address : 34, Yongam-gil, Chongryang-myeon, Ulju-gun, Ulsan 44989 Korea



※ You can verify the forgery and authenticity by the barcode at the end of this document.

TEST REPORT
(시험 성적서)

발행면수 (PAGE) : 3 of 11

발행일자 (DATE) : 2022. 05. 09.

시험성적서 번호 (REPORT NO.) : RT22R-S2395-K

시료고유번호 (SAMPLE ID NO.) : RT22R-S2395

시료명 (SAMPLE DESCRIPTION) : Cu Alloy PMC90 + Ag Plating
(Cu Alloy PMC90 + Ag Plating)

시험항목 (TEST ITEM)	단위 (UNIT)	분석방법 (TEST METHOD)	검출한계 (MDL)	시험결과 (RESULT)
폴리브롬화비페닐 (Polybrominated Biphenyls, PBBs)				
모노브로모비페닐 (MonoBB)	mg/kg	With reference to IEC 62321-6 Edition 1.0 : 2015, by solvent extraction and determined by GC/MS	5	N.D.
다이브로모비페닐 (DiBB)	mg/kg		5	N.D.
트라이브로모비페닐 (TriBB)	mg/kg		5	N.D.
테트라브로모비페닐 (TertaBB)	mg/kg		5	N.D.
펜타브로모비페닐 (PentaBB)	mg/kg		5	N.D.
헥사브로모비페닐 (HexaBB)	mg/kg		5	N.D.
헵타브로모비페닐 (HeptaBB)	mg/kg		5	N.D.
옥타브로모비페닐 (OctaBB)	mg/kg		5	N.D.
노나브로모비페닐 (NonaBB)	mg/kg		5	N.D.
데카브로모비페닐 (DecaBB)	mg/kg		5	N.D.
폴리브롬화디페닐에테르 (Polybrominated Diphenyl Ethers, PBDEs)				
모노브로모디페닐에테르 (MonoBDE)	mg/kg	With reference to IEC 62321-6 Edition 1.0 : 2015, by solvent extraction and determined by GC/MS	5	N.D.
다이브로모디페닐에테르 (DiBDE)	mg/kg		5	N.D.
트라이브로모디페닐에테르 (TriBDE)	mg/kg		5	N.D.
테트라브로모디페닐에테르 (TetraBDE)	mg/kg		5	N.D.
펜타브로모디페닐에테르 (PentaBDE)	mg/kg		5	N.D.
헥사브로모디페닐에테르 (HexaBDE)	mg/kg		5	N.D.
헵타브로모디페닐에테르 (HeptaBDE)	mg/kg		5	N.D.
옥타브로모디페닐에테르 (OctaBDE)	mg/kg		5	N.D.
노나브로모디페닐에테르 (NonaBDE)	mg/kg		5	N.D.
데카브로모디페닐에테르 (DecaBDE)	mg/kg		5	N.D.

Tested by : EH Cha

Notes : mg/kg = ppm = parts per million (함량 표시 : 백만분의 일)
 < = Less than (결과 값 이하)
 N.D. = Not detected (< MDL, 미검출 - 검출한계 이하)
 MDL = Method detection limit (검출한계)

Intertek Testing Services Korea Ltd.

Seoul Office: Tel : 02-6090-9500 Fax : 02-3409-0025 Web Site : intertek.co.kr

Seoul Lab. Address : 7, Ahasan-ro 5-gil, Seongdong-gu, Seoul, 04793 Korea

Ulsan Lab. Address : 34, Yongam-gil, Chongryang-myeon, Ulju-gun, Ulsan 44989 Korea



※ You can verify the forgery and authenticity by the barcode at the end of this document.

TEST REPORT
(시험 성적서)

발행면수 (PAGE) : 4 of 11

시험성적서 번호 (REPORT NO.) : RT22R-S2395-K

발행일자 (DATE) : 2022. 05. 09.

시료고유번호 (SAMPLE ID NO.) : RT22R-S2395

시료명 (SAMPLE DESCRIPTION) : Cu Alloy PMC90 + Ag Plating
(Cu Alloy PMC90 + Ag Plating)

시험항목 (TEST ITEM)	CAS번호 (CAS NO.)	단위 (UNIT)	분석방법 (TEST METHOD)	검출한계 (MDL)	시험결과 (RESULT)
프탈레이트 (Phthalates)					
Dibutyl phthalate (DBP)	84-74-2	mg/kg	With reference to IEC 62321-8 Edition 1.0 : 2017, by solvent extraction and determined by GC/MS	50	N.D.
Di(2-ethylhexyl) phthalate (DEHP)	117-81-7	mg/kg		50	N.D.
Benzyl butyl phthalate (BBP)	85-68-7	mg/kg		50	N.D.
Diisobutyl phthalate (DIBP)	84-69-5	mg/kg		50	N.D.

Tested by : EH Cha

Notes : mg/kg = ppm = parts per million (함량 표시 : 백만분의 일)
 < = Less than (결과 값 이하)
 N.D. = Not detected (< MDL, 미검출 - 검출한계 이하)
 MDL = Method detection limit (검출한계)

Intertek Testing Services Korea Ltd.

Seoul Office: Tel : 02-6090-9500 Fax : 02-3409-0025 Web Site : intertek.co.kr

Seoul Lab. Address : 7, Ahasan-ro 5-gil, Seongdong-gu, Seoul, 04793 Korea

Ulsan Lab. Address : 34, Yongam-gil, Chongryang-myeon, Ulju-gun, Ulsan 44989 Korea



※ You can verify the forgery and authenticity by the barcode at the end of this document.

TEST REPORT
(시험 성적서)

발행면수 (PAGE) : 5 of 11

시험성적서 번호 (REPORT NO.) : RT22R-S2395-K

발행일자 (DATE) : 2022. 05. 09.

시료고유번호 (SAMPLE ID NO.) : RT22R-S2395

시료명 (SAMPLE DESCRIPTION) : Cu Alloy PMC90 + Ag Plating
(Cu Alloy PMC90 + Ag Plating)

시험항목 (TEST ITEM)	단위 (UNIT)	분석방법 (TEST METHOD)	검출한계 (MDL)	시험결과 (RESULT)
베릴륨 (Beryllium, Be)	mg/kg	With reference to US EPA 3052, by acid digestion and determined by ICP-OES	2	N.D.
안티몬 (Antimony, Sb)	mg/kg	With reference to US EPA 3052, by acid digestion and determined by ICP-OES	2	N.D.
브롬 (Bromine, Br)	mg/kg	With reference to EN 14582, by oxygen combustion with bomb and determined by IC	30	N.D.
염소 (Chlorine, Cl)	mg/kg	With reference to EN 14582, by oxygen combustion with bomb and determined by IC	30	N.D.
퍼플루오로옥탄설포네이트 (Perfluorooctane sulfonate, PFOS)	mg/kg	With reference to US EPA 3550C/8321B, by ultrasonic Extraction and determined by LC/MS/MS	0.1	N.D.
퍼플루오로옥타노익에시드 (Perfluorooctanoic acid, PFOA)	mg/kg	With reference to US EPA 3550C/8321B, by ultrasonic Extraction and determined by LC/MS/MS	0.025	N.D.

Tested by : EH Cha, KH Kim, Hayan Park

Notes : mg/kg = ppm = parts per million (함량 표시 : 백만분의 일)
 < = Less than (결과 값 이하)
 N.D. = Not detected (< MDL, 미검출 - 검출한계 이하)
 MDL = Method detection limit (검출한계)

Intertek Testing Services Korea Ltd.

Seoul Office: Tel : 02-6090-9500 Fax : 02-3409-0025 Web Site : intertek.co.kr

Seoul Lab. Address : 7, Ahasan-ro 5-gil, Seongdong-gu, Seoul, 04793 Korea

Ulsan Lab. Address : 34, Yongam-gil, Chongryang-myeon, Ulju-gun, Ulsan 44989 Korea



※ You can verify the forgery and authenticity by the barcode at the end of this document.

TEST REPORT (시험 성적서)

발행면수 (PAGE) : 6 of 11


발행일자 (DATE) : 2022. 05. 09.

시험성적서 번호 (REPORT NO.) : RT22R-S2395-K

시료고유번호 (SAMPLE ID NO.) : RT22R-S2395

시료명 (SAMPLE DESCRIPTION) : Cu Alloy PMC90 + Ag Plating
(Cu Alloy PMC90 + Ag Plating)

* 시료 접수 시 시료 상태 :
(View of sample as received)



Intertek Testing Services Korea Ltd.

Seoul Office: Tel : 02-6090-9500 Fax : 02-3409-0025 Web Site : intertek.co.kr

Seoul Lab. Address : 7, Achasan-ro 5-gil, Seongdong-gu, Seoul, 04793 Korea

Ulsan Lab. Address : 34, Yongam-gil, Chongryang-myeon, Ulju-gun, Ulsan 44989 Korea



※ You can verify the forgery and authenticity by the barcode at the end of this document.

TEST REPORT

(시험성적서)

발행면수 (PAGE) : 7 of 11


시험성적서 번호 (REPORT NO.) : RT22R-S2395-K

발행일자 (DATE) : 2022. 05. 09.

시료고유번호 (SAMPLE ID NO.) : RT22R-S2395

시료명 (SAMPLE DESCRIPTION) : Cu Alloy PMC90 + Ag Plating
(Cu Alloy PMC90 + Ag Plating)

Flow Chart (IEC62321 Edition 1.0)



Remarks :

*1 : List of appropriate acid :

Material	Acid added for digestion
Polymers	HNO ₃ , HCl, HF, H ₂ O ₂ , H ₃ BO ₃
Metals	HNO ₃ , HCl, HF
Electronics	HNO ₃ , HCl, H ₂ O ₂ , HBF ₄

*2 : The samples were dissolved totally by pre-conditioning method according to above flow chart.

Intertek Testing Services Korea Ltd.

Seoul Office: Tel : 02-6090-9500 Fax : 02-3409-0025 Web Site : intertek.co.kr

Seoul Lab. Address : 7, Ahasan-ro 5-gil, Seongdong-gu, Seoul, 04793 Korea

Ulsan Lab. Address : 34, Yongam-gil, Chongryang-myeon, Ulju-gun, Ulsan 44989 Korea



※ You can verify the forgery and authenticity by the barcode at the end of this document.

TEST REPORT
(시험 성적서)

발행면수 (PAGE) : 8 of 11


발행일자 (DATE) : 2022. 05. 09.

시험성적서 번호 (REPORT NO.) : RT22R-S2395-K

시료고유번호 (SAMPLE ID NO.) : RT22R-S2395

시료명 (SAMPLE DESCRIPTION) : Cu Alloy PMC90 + Ag Plating
(Cu Alloy PMC90 + Ag Plating)

Flow Chart (Phthalates)



Intertek Testing Services Korea Ltd.

Seoul Office: Tel : 02-6090-9500 Fax : 02-3409-0025 Web Site : intertek.co.kr

Seoul Lab. Address : 7, Ahasan-ro 5-gil, Seongdong-gu, Seoul, 04793 Korea

Ulsan Lab. Address : 34, Yongam-gil, Chongryang-myeon, Ulju-gun, Ulsan 44989 Korea



※ You can verify the forgery and authenticity by the barcode at the end of this document.

TEST REPORT (시험 성적서)

발행면수 (PAGE) : 9 of 11


시험성적서 번호 (REPORT NO.) : RT22R-S2395-K

발행일자 (DATE) : 2022. 05. 09.

시료고유번호 (SAMPLE ID NO.) : RT22R-S2395

시료명 (SAMPLE DESCRIPTION) : Cu Alloy PMC90 + Ag Plating
(Cu Alloy PMC90 + Ag Plating)

Flow Chart (Metal Testing)



** Remarks : The samples were dissolved totally by pre-conditioning method according to above flow chart.

Intertek Testing Services Korea Ltd.

Seoul Office: Tel : 02-6090-9500 Fax : 02-3409-0025 Web Site : intertek.co.kr

Seoul Lab. Address : 7, Achasan-ro 5-gil, Seongdong-gu, Seoul, 04793 Korea

Ulsan Lab. Address : 34, Yongam-gil, Chongryang-myeon, Ulju-gun, Ulsan 44989 Korea



※ You can verify the forgery and authenticity by the barcode at the end of this document.

TEST REPORT

(시험 성적서)

발행면수 (PAGE) : 10 of 11


발행일자 (DATE) : 2022. 05. 09.

시험성적서 번호 (REPORT NO.) : RT22R-S2395-K

시료고유번호 (SAMPLE ID NO.) : RT22R-S2395

시료명 (SAMPLE DESCRIPTION) : Cu Alloy PMC90 + Ag Plating
(Cu Alloy PMC90 + Ag Plating)

Flow Chart (Halogen)



Intertek Testing Services Korea Ltd.

Seoul Office: Tel : 02-6090-9500 Fax : 02-3409-0025 Web Site : intertek.co.kr

Seoul Lab. Address : 7, Ahasan-ro 5-gil, Seongdong-gu, Seoul, 04793 Korea

Ulsan Lab. Address : 34, Yongam-gil, Chongryang-myeon, Ulju-gun, Ulsan 44989 Korea



※ You can verify the forgery and authenticity by the barcode at the end of this document.

TEST REPORT

(시험성적서)

발행면수 (PAGE) : 11 of 11


시험성적서 번호 (REPORT NO.) : RT22R-S2395-K

발행일자 (DATE) : 2022. 05. 09.

시료고유번호 (SAMPLE ID NO.) : RT22R-S2395

시료명 (SAMPLE DESCRIPTION) : Cu Alloy PMC90 + Ag Plating
(Cu Alloy PMC90 + Ag Plating)

Flow Chart (PFOS, PFOA)



***** End of Report *****

Except where explicitly agreed in writing, all work and services performed by Intertek is subject to our standard Terms and Conditions which can be obtained at our website: <http://www.intertek.com/terms/>. Intertek's responsibility and liability are limited to the terms and conditions of the agreement.

This report is made solely on the basis of your instructions and / or information and materials supplied by you and provide no warranty on the tested sample(s) be truly representative of the sample source. The report is not intended to be a recommendation for any particular course of action, you are responsible for acting as you see fit on the basis of the report results. Intertek is under no obligation to refer to or report upon any facts or circumstances which are outside the specific instructions received and accepts no responsibility to any parties whatsoever, following the issue of the report, for any matters arising outside the agreed scope of the works. This report does not discharge or release you from your legal obligations and duties to any other person. You are the only one authorized to permit copying or distribution of this report (and then only in its entirety). Any such third parties to whom this report may be circulated rely on the content of the report solely at their own risk.

This report shall not be reproduced, except in full.
This report is not related to the scope of Korea Laboratory Accreditation Scheme.

Intertek Testing Services Korea Ltd.

Seoul Office: Tel : 02-6090-9500 Fax : 02-3409-0025 Web Site : intertek.co.kr

Seoul Lab. Address : 7, Ahasan-ro 5-gil, Seongdong-gu, Seoul, 04793 Korea

Ulsan Lab. Address : 34, Yongam-gil, Chongryang-myeon, Ulju-gun, Ulsan 44989 Korea



※ You can verify the forgery and authenticity by the barcode at the end of this document.